

Non-destructive examination of fusion welds
Visual examination
English version of DIN EN 970

DIN
EN 970

ICS 25.160.40

Descriptors: Testing, welded joints, visual examination, metals.

Zerstörungsfreie Prüfung von Schmelzschweißnähten – Sichtprüfung

European Standard EN 970:1997 has the status of a DIN Standard.

A comma is used as the decimal marker.

National foreword

This standard has been prepared by CEN/TC 121.

The responsible German body involved in its preparation was the *Normenausschuß Schweißtechnik* (Welding Standards Committee).

EN comprises 13 pages.

ICS 25.160.40

Descriptors: Testing, welded joints, visual examination, metals.

English version

Non-destructive examination of fusion welds
Visual examination

Contrôle non destructif des assemblages soudés par fusion – contrôle visuel Zerstörungsfreie Prüfung von Schmelzschweißnähten – Sichtprüfung

This European Standard was approved by CEN on 1996-12-12.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Contents

	Page
Foreword	2
1 Scope	3
2 Normative references	3
3 Examination conditions and equipment	3
4 Personnel	4
5 Visual examination - General	4
6 Visual examination of joint preparation	5
7 Visual examination during welding	5
8 Visual examination of the finished weld	5
8.1 General	5
8.2 Cleaning and dressing.....	6
8.3 Profile and dimensions.....	6
8.4 Weld root and surfaces	6
8.5 Post-weld heat treatment	7
9 Visual examination of repaired welds	7
9.1 General	7
9.2 Partially removed weld	7
9.3 Completely removed weld	7
9.4 Examination.....	7
10 Examination records	7
Annex A (informative) Examples of examination equipment	9

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 1997, and conflicting national standards shall be withdrawn at the latest by August 1997.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

It should be noticed that a standard covering the general principles of visual examination is under preparation by CEN/TC 138.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard covers the visual examination of fusion welds in metallic materials. The examination is normally performed on welds in the as-welded condition but exceptionnally, for example when required by an application standard or by agreement between the contracting parties, the examination may be carried out at other stages during the welding process.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 288-2		Specification and approval of welding procedures for metallic materials - Part 2 : Welding procedure specification for arc welding
EN 473		Qualification and certification of NDT personnel - General principles
prEN 12062		Non-destructive examination of welds - General rules
EN 25817		Arc-welded joints in steel - Guidance on quality levels for imperfections (ISO 5817:1992)
EN 30042		Arc-welded joints in aluminium and its weldable alloys - Guidance on quality levels for imperfections (ISO 10042:1992)
ISO 3058 :	1974	Non-destructive testings - Aids to visual inspection - Selection of low power magnifiers
ISO 3599 :	1976	Vernier callipers reading to 0,1 and 0,05 mm

3 Examination conditions and equipment

The illuminance at the surface, shall be a minimum of 350 lx, 500 lx are recommended.

For performance of direct inspection, the access shall be sufficient to place the eye within 600 mm of the surface to be examined and at an angle not less than approximately 30 ° (see figure 1).




Figure 1 : Access for examination

Remote inspection using boroscopes, fibre optics or cameras shall be considered as additional requirements and be specified by an application standard or by agreement between the contracting parties.

If required to obtain a good contrast and relief effect between imperfections and background, an additional light source should be used.

In case of doubt, visual examination should be supplemented by other non-destructive testing methods for surface inspections.

Examples of examination equipment are given in annex A.

4 Personnel

Personnel who carry out examination in accordance with this European Standard should :

- a) be familiar with relevant standards, rules and specifications ;
- b) be informed about the welding procedure to be used ;
- c) have a good vision in accordance with the requirements of EN 473, which should be checked every 12 months.

5 Visual examination - General

The extent of examination shall be defined in advance by an application standard or by agreement between the contracting parties.

The examiner shall have access to the necessary inspection and production documentation required.

Welds shall be examined in the as-welded condition while physical access is possible and sometimes it is also necessary to examine surface treatments.

6 Visual examination of joint preparation

When visual examination is required prior to welding, the welds shall be examined to check that :

- a) the shape and dimensions of the weld preparation meet the specified requirements given in the welding procedure specification, e.g. in accordance with EN 288-2 ;
- b) the fusion faces and adjacent surfaces are cleaned ;
- c) the parts to be joined by welding are fixed in relation to each other according to drawings or instructions.

7 Visual examination during welding

When required, the weld shall be examined during the welding process to check that :

- a) each run or layer of weld metal is cleaned before it is covered by a further run, particular attention being paid to the junctions between the weld metal and the fusion face ;
- b) there are no visible imperfections, e.g. cracks or cavities ; if such imperfections are observed, they shall be reported so that remedial action can be taken before the deposition of further weld metal ;
- c) the transition between the runs and between the weld and the parent metal has such a shape that satisfactory melting can be accomplished when welding the next run ;
- d) the depth and shape of gouging is in accordance with the WPS or compared with the original groove shape in order to assure complete removal of the weld metal as specified.

8 Visual examination of the finished weld

8.1 General

The finished weld shall be examined to determine whether it meets the agreed acceptance standard, e.g. EN 25817 or EN 30042 or by reference to prEN 12062. If not specifically included within the requirements of an application standard or by agreement between the contracting parties, the items detailed in 8.2 to 8.5 shall be checked.

8.2 Cleaning and dressing

The weld shall be examined to check that :

- a) all slag has been removed by manual or mechanical means. This is to avoid imperfections from being obscured ;
- b) there are no tool impressions or blow marks ;
- c) when weld dressing is required, overheating of the joint due to grinding is avoided and that grinding marks and an uneven finish are also avoided ;
- d) for fillet welds and butt welds to be dressed flush, the joint merges smoothly with the parent metal without under flushing.

8.3 Profile and dimensions

The weld shall be examined to check that :

- a) the profile of the weld face and the height of any excess weld metal meet the requirements of the acceptance standard (see 8.1) ;
- b) the surface of the weld is regular, the pattern and the pitch of weave marks present an even and satisfactory visual appearance. The distance between the last layer and the parent metal or the position of runs has been measured where required by the WPS ;
- c) the weld width is consistent over the whole of the joint and that it meets the requirements given in the weld drawing or acceptance standard (see 8.1). In the case of butt welds, it shall be checked that the weld preparation has been completely filled.

8.4 Weld root and surfaces

The visually accessible parts of the weld, i.e. the weld root for a single-sided butt weld and the weld surfaces, shall be examined for deviations from the acceptance standard (see 8.1).

The weld shall be examined to check that :

- a) in the case of single-sided butt welds, the penetration, root concavity and any burn-through or shrinkage grooves are within the limits specified in the acceptance standard over the whole of the joint ;
- b) any undercut is within the acceptance standard ;
- c) any imperfections such as cracks or porosity detected, using optical aids when necessary, in the weld surface or heat affected zones comply with the appropriate acceptance criteria ;
- d) any attachments temporarily welded to the object to facilitate production or assembly which are prejudicial to the function of the object or the ability to examine it, are removed so that the object is not damaged. The area where the attachment was fixed shall be checked to ensure freedom of cracks.

8.5 Post-weld heat treatment

Further examination may be required after post-weld heat treatment.

9 Visual examination of repaired welds

9.1 General

When welds fail to comply wholly or in part with the acceptance criteria and repair is necessary, the checks detailed in 9.2 and 9.3 shall be made during repair operation.

9.2 Partially removed weld

It shall be checked that the excavation is sufficiently deep and long to remove all imperfections. It shall also be ensured that there is a gradual taper from the base of the cut to the surface of the weld metal at the ends and sides of the cut, the width and profile of the cut being such that there is adequate access for re-welding.

9.3 Completely removed weld

It shall be checked that, when a cut has been made through a faulty weld and there has been no serious loss of material, or when a section of materials containing a faulty weld has been removed and a new section is to be inserted, the shape and dimensions of the weld preparation meet the specified requirements.

9.4 Examination

Every repaired weld shall be examined to the same requirements as the original weld, as specified in clause 8.

10 Examination records

It is not always necessary to keep a record of the examination. However, when specified, a record should be kept to show that every relevant item of the visual examination at each stage has been checked. The following lists the information that should be included in the report :

- a) name of the component manufacturer ;
- b) name of the examining body, if different from a) ;
- c) identification of the object examined ;
- d) material ;
- e) type of joint ;

- f) material thickness ;**
- g) welding process ;**
- h) acceptance criteria ;**
- i) imperfections exceeding the acceptance criteria and their location ;**
- j) the extent of examination with reference to drawings as appropriate ;**
- k) examination devices used ;**
- l) result of examination with reference to acceptance criteria ;**
- m) name of examiner and date of examination.**

Where required, welds that have been examined and approved should be suitably marked or identified.

When it is required to have a permanent visual record of a weld as examined, photographs or accurate sketches or both should be made with any imperfections clearly indicated.

Annex A (informative)

Examples of examination equipment

Equipments used to carry out measurements may be selected from the following :

- a) straight edge or measuring tape with a graduation of 1 mm or finer ;
- b) vernier caliper according to ISO 3599 ;
- c) feeler gauge with a sufficient number of feelers to measure dimensions between 0,1 mm and 3 mm in steps of at most 0,1 mm ;
- d) radius gauge ;
- e) magnifying lens with a magnification 2 x to 5 x ; the lens should preferably have a scale, see ISO 3058.



Following equipments may also be needed :

- 1) profile measuring device with a wire diameter or width ≤ 1 mm, where each wire end is rounded ;
- 2) material for impression of welds, e.g. coldsetting plastic or clay ;
- 3) for visual inspection of welds with limited accessibility, mirrors, endoscopes, boroscopes, fibre optics or TV-cameras may be used ;
- 4) any other measurement device agreed by the contracting parties, i.e. specifically designed welding gauges, height/depth gauges, rulers or protactors.

Typical measurement devices and gauges are detailed in table A.1.




NOTE: These devices and gauges are detailed purely as examples of examination equipment. Some of the designs may be registered designs or the subject of patents.

Table A.1 : Measuring instruments and weld gauges - measuring ranges and reading accuracy

Weld gauge	Description	Type of weld				Measuring range mm	Reading accuracy mm	Included or fillet angle degree	Permissible deviation of included or fillet angle
		Fillet weld		Convex weld	Butt weld				
		Flat weld	Concave weld						
	<p>Simple weld gauge</p> <p>a) Measures fillet weld from 3 to 15 mm thickness. The gauge will be placed by the curved part in the fusion faces so as to have three points of contact with the work piece and the fillet weld.</p> <p>b) Measures butt welds reinforcement with the straight part.</p> <p>Because the gauges consists of relative soft aluminium they wear out rapidly.</p>	x	x	-	x	3 to 15	≈ 0,5	90	small
	<p>Set of welding gauges</p> <p>Measures fillet welds from 3 to 12 mm thickness ; from 3 to 7 mm : graduations of 0,5 mm ; above 8 mm, 10 mm and 12 mm. The gauge measures by using the principle of three-point contact.</p>	x	x	-	-	3 to 12	according to fan part	90	none




(to be continued)

Table A.1 (continued)

Weld gauge	Description	Type of weld				Measuring range mm	Reading accuracy mm	Included or fillet angle degree	Permissible deviation of included or fillet angle
		Fillet weld		Convex weld	Butt weld				
		Flat weld	Concave weld						
	Weld gauge with vernier Measures fillet welds ; also reinforcement of butt welds can be determined. The legs of the gauge are so formed that included angles of 60 °, 70 °, 80 ° and 90 ° of V- and single-V butt weld with broad face can be measured. But slight deviations from these lead to significant errors.	x	x	-	x	0 to 20	0,1	90	none
	Self made weld gauge Measures 7 throat thickness of fillet welds with an included angle of 90 °.	x	-	-	-	0 to 20	0,2	90	none
	Three-scale weld gauge Measures throat thickness and leg length. Can also measure weld reinforcement of butt welds. Easy to use. Also appropriate for asymmetric fillet welds.	x	x	x	x	0 to 15	0,1	90	small




(to be continued)

Table A.1 (continued)

Weld gauge	Description	Type of weld				Measuring range mm	Reading accuracy mm	Included or fillet angle degree	Permissible deviation of included or fillet angle
		Fillet weld		Convex weld	Butt weld				
		Flat weld	Concave weld						
	Gauge for checking profile of fillet welds Checking the profile of one shape for one size of fillet welds. This type of gauge needs one model for each size of fillet weld.	-	-	-	-	-	-	-	
	Multi purpose gauge Measures angle of bevel, leg length of fillet weld, undercut, misalignment, throat thickness and weld reinforcement.	x	x	x	0 to 50	0,3	0 to 45 (angle of bevel)	none	
	Universal weld gauge Measures tasks : - fillet welds : shape and dimensions. - butt welds : misalignment of plates, joint preparation (angle width), weld reinforcement, weld width, undercuts.	x	x	x	0 to 30	0,1	-	± 25 %	

(to be continued)

Table A.1 (concluded)

Weld gauge	Description	Type of weld				Measuring range mm	Reading accuracy mm	Included or fillet angle degree	Permissible deviation of included or fillet angle
		Fillet weld			Butt weld				
		Flat weld	Concave weld	Convex weld					
	Gap gauge Measures the width of gaps.	-	-	-	x	0 to 6	0,1	-	-
	Hook gauge for misalignment Measures the misalignment of the preparation for butt welds on plates and pipes.	-	-	-	x	0 to 100	0,05	-	-
	Universal butt weld gauge Measures the preparation and the finished butt weld : (1) angle of bevel, (2) width of root gap, (3) weld reinforcement, (4) width of weld surface (5) depth of undercut (6) diameter of consumables.	x	x	x	x	0 to 30	0,1	-	± 25 %